

# 750°F GRAY

## RTV GASKET MAKER (NEUTRAL)



ISO 9001

**DESCRIPTION:**

**x'traseal® 750°F GRAY RTV GASKET MAKER** IS A ONE PART SILICONE SEALANT THAT CURE TO FORM A DURABLE RUBBER SEAL THAT OFFER EXCELLENT ADHESION, HEAT RESISTANT FOR GLAZING AND JOINT SEALING APPLICATION.

**FEATURES:**

- ◆ LOW ODOR NEUTRAL CURING SYSTEM.
- ◆ NON-CORROSIVE TO METALS.
- ◆ NON-CORROSIVE TO AUTOMOBILES.
- ◆ OUTSTANDING HIGH TEMPERATURE RESISTANT UPTILL 399°C.
- ◆ EXCELLENT GUNNABILITY (-20°C TO 50°C).
- ◆ PRIMERLESS ADHESION TO MOST MATERIALS.

**USES:**

- ◆ HIGH TEMPERATURE RESISTANT GASKET AND JOINT SEALING.
- ◆ ASSEMBLIES OF GLASS, PORCELAIN COATED METAL, EPOXY AND POLYESTER PANELS, POLYSTYRENE, ANODISED ALUMINIUM AND FINISHED WOOD.

**WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS**

**NOT RECOMMENDED FOR:**

NOT FOR: 750°F XTRA GRAY RTV SILICONE IS NOT PAINTABLE.  
 NOT FOR: PE, PP, PTFE AND BITUMINOUS SURFACE.  
 NOT FOR: PARTS IN CONTACT WITH GASOLINE.

- ◆ REMOVE OLD GASKET MATERIAL FROM SURFACES THOROUGHLY.
- ◆ CLEAN SURFACE WITH RESIDUE-FREE SOLVENT AND ALLOW SURFACE TO DRY.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ SQUEEZE TUBE TO FORM A CONTINUOUS AND EVEN BEAD TO THE PERIMETER OF MATING SURFACE AND ALL BOLT HOLES.
- ◆ TOOL WITHIN 5 MINUTES.
- ◆ TIGHTENED TO THE REQUIRED TORQUE, DO NOT OVERTIGHTEN.
- ◆ CLEAN OFF EXCESS SEALANT WITH M.E.K. OR TOLUENE.

**CURING TIME:**

750°F XTRA GRAY RTV SILICONE WILL TACK FREE IN APPROXIMATELY 20 MINUTES AND WILL CURE TO A DEPTH OF 13mm WITHIN 7 DAYS. LONGER CURING TIME MAY BE NECESSARY IN DRY AND LOW HUMIDITY AREA.

**SPECIFICATION:**

CURING SYSTEM	NEUTRAL (OXIME)
APPEARANCE	NON-SAGGING PASTE
ODOUR	OXIME SMELL
SPECIFIC GRAVITY	1.04 ± 0.03
SHORE A HARDNESS	30 APPROX.
ELONGATION	400% APPROX.
TENSILE STRENGTH	2.0MPa APPROX.
TOOLING TIME	5 MINUTES
TACK FREE TIME	20 MINUTES
APPLICATION TEMP.	-20°C TO 50°C
SERVICE TEMPERATURE	-40°C TO 399°C.
SHELF LIFE	12 MONTHS

**STORAGE:**

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

**APPLICATION:**



# 750°F GRAY

## RTV GASKET MAKER (NEUTRAL)



ISO 9001

**CAUTION:**

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

*This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.*

